

Enviroshade



ROLLER



PANEL

Technical Data

Composition	100% Trevira-CS (PVC free)
Width	2,400mm
Weight	155gsm +/-5%
Thickness	0.40mm +/-5%
Opacity/Openness	Specific to colour (see PDF)
Light fastness	Specific to colour (see PDF)
Coating	Aluminium (for aluminised options only)
Flame Retardant	AWTA AS1530.3 German Standard DIN 4102 B1 French Standard M1
Cleaning	Surface dust can be removed with vacuum or a soft cloth

textstyle.com.au

Phone. 03 9729 9970



Solar Properties - Enviroshade

	USA Standard Tested To Ashrae 74-73									
	Ts	Rs	As	Tv/ Vlt	Tuv	O-F	Shading Coefficients (Sc)			
							3mm CL.	6mm CL.	6mm H.A	
Arctic	45	55	0	46	18	5	0.45	0.26	0.82	
Beige	36	61	3	34	13	5	0.41	0.26	0.80	
Mercury	36	53	11	27	14	5	0.45	0.26	0.83	
Icon	24	37	39	7	7	4	0.53	0.28	0.87	
Raven	23	33	44	5	6	4	0.55	0.28	0.88	
Shimmer	26	40	34	9	9	4	0.51	0.28	0.86	
Walnut	23	34	43	6	5	4	0.55	0.28	0.88	
Stone	27	43	30	11	8	5	0.50	0.27	0.85	
Bronze/Pearl	28	48	24	12	12	5	0.47	0.27	0.84	

Ts Solar Transmittance **As** Solar Absorbance **Tuv** Ultraviolet Transmittance
Rs Solar Reflection **Tv** Visual Light Transmission

Solar Properties - Enviroshade Aluminium

	USA Standard Tested To Ashrae 74-73									
	Ts	Rs	As	Tv/ Vlt	Tuv	O-F	Shading Coefficients (Sc)			
							3mm CL.	6mm CL.	6mm H.A	
Arctic	11	57	36	12	8	4	0.39	0.26	0.81	
Beige	10	58	32	12	6	4	0.39	0.26	0.80	
Mercury	9	56	35	10	5	4	0.40	0.26	0.81	
Icon	8	53	39	5	6	4	0.41	0.26	0.82	
Raven	8	53	39	5	5	4	0.41	0.26	0.82	
Shimmer	8	54	38	5	6	4	0.41	0.26	0.81	
Walnut	8	54	38	5	4	4	0.41	0.26	0.81	
Stone	8	55	37	6	6	4	0.40	0.26	0.81	
Bronze/Pearl	8	52	40	7	6	4	0.47	0.27	0.84	

Ts Solar Transmittance **As** Solar Absorbance **Tuv** Ultraviolet Transmittance
Rs Solar Reflection **Tv** Visual Light Transmission